


Screen Goo Projection Screen Coatings



Ultra Silver 3D Finish Coating

<u>Description</u>	<u>Characteristics</u>	<u>Specifications</u>
<p>Screen Goo Ultra Silver 3D Finish Coating is the polarity preserving component of the Screen Goo 3D two part video projection screen system; to be used in conjunction with, and applied subsequently to, Screen Goo Max Contrast Reflective Coating.</p> <p>Advantages</p> <ul style="list-style-type: none">– ASTM D4236 approved non-toxic water base acrylic coating– ASTM E-84-06 approved for fire safety– No California Proposition 65 Statement required– VOC: 73g/1000mL (per ASTM D3960 method)– lead-free– premium, colour fast pigments– museum grade 100 % acrylic base– very durable– polarity preserving– very reflective– not degraded by UV light– strongly resistant to yellowing– spray application only– suitable for indoor and outdoor use	<p>Gloss: 3.8 Volume Solids: 36.5-38.5 Viscosity: 26 seconds # 3 Zahn cup Recommended film thickness: Mils Wet: 1.5 Mils Dry: 0.50 Spreading Rate (no application loss): 302.4 sq ft/gal @ (recommended Mils Dry Film Thickness) Drying (25° C/77°F; 45% RH): To Touch: 1 hour To Handle: 24 hrs. To Sand: not recommended To Re-coat: 4 hours Force Dry: not recommended Curing temperature should not exceed 40°C/104°F Mixing Ratio: N/A Pot Life: N/A Flash Point: will not ignite; may boil at > 100°C/212°F Package Life: 5 years unopened</p> 	<p>General: Substrate should be free of grease, oil, dirt, fingerprints and other contaminants. Drywall: Level 5 finish required. Prime with quality white primer compatible with water based over-coating. Wood Products: Level 5 finish required. Prime with quality white primer compatible with water based over-coating. Fabrics: Will adhere correctly and permanently to all natural fibre materials: canvas, muslin, etc. Not recommended for application to PVC, polyester and any substrate containing solvents or volatile plasticizers.</p> <p><u>Application Notes</u></p> <p><u>Two coat application required</u></p> <p>Rolled: not recommended.</p> <p>Sprayed: Use an HVLP system for application <50 sq. ft; 1.5-2mm tip diameter. 40-45 psi. For applications > 50sq. ft, use industrial capacity airless system: 12 -14 fan spray tip; piston pump; maximum 50 ft. of hose; ¾ gpm capacity. Still air required for best results, minimize air circulation while applying.</p>